



FIERRO Y ACERO
COFIASA

Lámina Negra



Calibre	Espesor		Peso teórico		Peso aproximado por hoja			
	Pulg.	Mm	Kg/m ²	Kg/pie ²	3 X 8	3 X 10	4 X 8	4 X 10
1/4	0.2500	6.35	49.83	4.63	111.12	138.89	148.16	185.19
3	0.2390	6.07	48.82	4.54	108.85	136.07	145.13	181.43
4	0.2242	5.69	45.77	4.25	102.05	127.57	136.07	170.09
5	0.2090	5.31	42.72	3.97	95.25	119.56	127.00	159.41
6	0.1938	4.92	39.67	3.69	88.45	110.56	117.93	147.42
3/16	0.1870	4.75	37.28	3.46	83.11	103.89	110.81	138.52
7	0.1790	4.55	36.62	3.4	81.65	102.06	108.87	136.08
8	0.1640	4.17	33.57	3.12	74.85	93.56	99.80	124.75
9	0.1495	3.80	30.52	2.84	68.05	85.06	90.73	113.42
10	0.1345	3.42	27.46	2.55	61.23	76.54	81.64	102.05
1/8	0.1250	3.18	24.92	2.31	55.56	69.45	74.08	92.60
11	0.1196	3.04	24.41	2.27	54.43	68.04	72.57	90.72
12	0.1046	2.66	21.36	1.98	47.63	59.54	63.51	79.38
13	0.0897	2.28	18.30	1.7	40.80	51.00	54.40	68.00
14	0.0747	1.90	15.26	1.42	34.02	42.53	45.36	56.70
15	0.0673	1.71	13.42	1.25	29.91	37.39	39.88	49.85
16	0.0598	1.52	12.20	1.13	27.20	34.00	36.27	45.33
17	0.0538	1.37	10.72	1	23.91	29.89	31.88	39.85
18	0.0478	1.21	9.76	0.91	21.76	27.20	29.01	36.27
19	0.0418	1.06	8.33	0.77	18.58	23.23	24.77	30.97
20	0.0359	0.91	7.32	0.68	16.32	20.40	21.76	27.20
21	0.0329	0.84	6.56	0.61	14.62	18.28	19.49	24.37
22	0.0299	0.76	6.10	0.57	13.60	17.00	18.13	22.67
23	0.0269	0.68	5.36	0.5	11.96	14.95	15.95	19.93
24	0.0239	0.61	4.88	0.45	10.88	13.60	14.51	18.13
25	0.0209	0.53	4.17	0.39	9.29	11.61	12.39	15.48
26	0.0179	0.45	3.66	0.34	8.16	10.20	10.88	13.60
27	0.0164	0.42	3.27	0.3	7.29	9.11	9.72	12.15
28	0.0149	0.38	3.05	0.28	6.80	8.50	9.07	11.33
29	0.0135	0.34	2.69	0.25	6.00	7.50	8.00	10.00
30	0.0120	0.30	2.44	0.23	5.44	6.80	7.25	9.07